

TECHNICAL DATA SHEET

Revision 2.2 Revision Date: 02/10/2020



Omega II Cored Solder Wire

Rosin and Halide Free Soldering

Description

Omega II Rosin Free Cored Solder Wire is a halide free flux core contained in Warton High Purity Cored Solder Wire. Containing no rosin (colophony), resin acids, pine oil or other naturally occurring derivatives from pine trees, it has been specifically designed to reduce the number of worldwide cases of industrial asthma, related to rosin usage within a cored solder wire. Omega II provides excellent wetting whilst leaving a minimal no clean, clear residue. Cleaning by batch or in-line processes is not suitable, however, if residues need to be removed use Warton Total Clean 130 cleaner.

Benefits

- No Clean
- Rosin Free
- Halide Free
- RELO Classification
- Minimal Clear Residues

Properties

Flux Classification (J-STD-004B)	RELO
Quantitative Halide (J-STD-004B) (IPC-TM-650 2.3.28)	Halide Free (0.05% Max)
Surface Insulation Resistance (J-STD-004B) (IPC-TM-650 2.6.3)	Pass
Electro Migration (Bellcore GR-78) (IPC-TM-650 2.6.14)	Pass
Copper Mirror Test (J-STD-004A/B) (IPC-TM-650 2.3.32)	Pass
Copper Corrosion Test (J-STD-004A/B) (IPC-TM-650 2.6.15)	Pass

Availability

Product	Flux Content	Standard Packaging
Omega II	1%, 2%, 3%	0.25Kg, 0.5Kg, 2.5Kg, 3Kg, 5Kg, 10Kg, 15Kg and 25Kg reels

Other packaging options available. For more information on alternate packaging options please contact our sales team.

TECHNICAL DATA SHEET

High Purity Solder Alloy

Standardization is important to reduce variety and to promote the quality of products by defining features and characteristics governing their fitness for purpose. The standards promote clear unambiguous communication between purchasers and suppliers for quotation ordering and supply purposes.

In 1994 a single European standard, EN 29453 (ISO 9453), superseded all other European national standards including: BS 219, DIN 1707, NFC 90-550. Other equivalent international standards include J-STD-006, ASTM B32 and JIS-Z-3382.

Warton High Purity Solder Alloys are manufactured using only the 'Highest Purity Virgin Materials' this being part of Warton's simple philosophy that the best raw materials lead to the best finished products.

Below shows a typical batch analysis of the High Purity Tin/Lead used in manufacturing High Purity 63/37.

Typical batch analysis: Tin

Sn	Sb	Pb	Cu	Zn
99.95	0.009	0.002	0.0002	0.0001
Fe	As	Ag	Bi	In
0.002	0.002	0.0001	0.0001	0.0003

Typical batch analysis: Lead

Sn	Sb	Pb	Cu	Zn
0.001	0.002	99.99	0.003	0.0001
Fe	As	Ag	Bi	In
0.002	0.0005	0.002	0.005	0.0003

Typical batch analysis: Warton High Purity 63/37

Sn	Sb	Pb	Cu	Zn	Fe	As	Ag	Bi	In
63.0	0.0095	remainder	0.0007	0.0002	0.002	0.001	0.0005	0.0003	0.0003

These consistent high standards apply not only to all of Warton's high purity solder alloys, but to its entire range of products, inclusive of flux cored and solid solders, liquid fluxes, cleaners and solder paste.

Lead Free Solder Alloys

In accordance with REACH legislation and increasing environmental awareness Warton Metals offer a complete range of 'lead free' alloys to suit all applications.

Warton's range of lead free solder alloys includes:

Alloy Name	Alloy Breakdown	Melting Temperature °C
Tin	Sn100	232
96S	Sn96.5/Ag3.5	221
96/4	Sn96/Ag4	221
98S	Sn98/Ag2	221-226
TSC	Sn95.8/Ag3.5/Cu0.7	217-218
SAC405	Sn95.5/Ag4/Cu0.5	217-219
Sc100e	Cu0.5-0.7/Sn Rem	227
LM10A	Sn87/Ag10/Cu3	214-275
SACXP0307	Sn/Cu0.7/Ag0.3	217-227
SAC0307	Sn99/Ag0.3/Cu0.7	217-227
SAC305	Sn96.5/Ag3/Cu0.5	217-220
SAC300	Sn97/Ag3	221-224
SAC3	Sn96.7/Ag2.8/Cu0.5	217-220
SAC2	Sn97.5/Ag2/Cu0.5	217-220
SAC1	Sn99.2/Ag0.3/Cu0.5	217-220
97C	Sn97/Cu3	227-310
99C	Sn99.3/Cu0.7	227
95A	Sb4.5-5.5/Sn Rem	235-240

Key: Sn-Tin, Ag-Silver, Cu-Copper, Rem-Remainder
Other alloys available

Leaded Solder Alloys

Warton are able to offer a comprehensive range of leaded solder alloys to 'Professional Users' which will be marked as **For Professional Use Only** in accordance with REACH regulations.

Warton's range of leaded solder alloys includes:

Alloy Name	Alloy Breakdown	Melting Temperature °C
60/40	Sn60/Pb40	183-190
63/37	Sn63/Pb37	183
50/50	Sn50/Pb50	183-215
45/55	Sn45/Pb55	183-226
40/60	Sn40/Pb60	183-238
35/65	Sn35/Pb65	183-245
30/70	Sn30/Pb70	183-255
20/80	Sn20/Pb80	183-280
Alloy 296 HMP	Sn5/Pb92/Ag3	296-301
15/85	Sn15/Pb85	226-290
LMP 62S	Sn62/Pb36/Ag2	179
TLS/5	Sn5/Pb94/Ag1	296-301
HMP 5S	Sn5/Pb93.5/Ag1.5	296-301
Sn10Pb88Ag2	Sn10/Pb88/Ag2	268-290
Alloy No1	Sn50/Pb48.6/Cu1.4	183-215
Alloy No2	Sn60/Pb38.2/Cu1.8	183-190
1/99	Sn1/Pb99	300
60/40 Ant	Sn60/Sb0.2-0.5/Pb Rem	183-188

Key: Sn-Tin, Pb-Lead, Ag-Silver, Cu-Copper, Sb-Antimony, Rem-Remainder
Other alloys available

Please note that not all alloys are available ex-stock and minimum order quantities may apply.

TECHNICAL DATA SHEET

Wire gauge (Diameter)

The wire gauge (diameter) for Warton solid and flux cored solder wires is represented as SWG (Standard Wire Gauge). The equivalent imperial and metric values are shown below.

SWG	mm	Inch
10	3.25	0.128
11	2.95	0.116
12	2.64	0.104
13	2.34	0.092
14	2.03	0.080
16	1.63	0.064
18	1.22	0.04
20	0.914	0.036
21	0.813	0.032
22	0.711	0.028
24	0.599	0.022
26	0.457	0.018
28	0.375	0.014
30	0.315	0.012
32	0.274	0.010
34	0.234	0.009
36	0.193	0.008

Other wire diameters available

Not all wire diameters available in all stocking units.

The information supplied in this technical data sheet is designed only as guidance for the safe use and handling of the product. This information is correct to the best of our knowledge and belief at the date of publication however no guarantee is made to its accuracy. This information related only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process.

